

# LEXAN™ COPOLYMER EXL8483

REGION ASIA

## DESCRIPTION

LEXAN EXL8483 is a PC/siloxane copolymer resin with medium flow, excellent low temperature impact and 80% post consumer recycle content. Limited availability and restricted color only. Higher color variability and contamination risks including black specs needs to be considered before approval for use in applications.

## TYPICAL PROPERTY VALUES

Revision 20210812

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 50 mm/min	57	MPa	ASTM D638
Tensile Stress, brk, Type I, 50 mm/min	55	MPa	ASTM D638
Tensile Strain, yld, Type I, 50 mm/min	6	%	ASTM D638
Tensile Strain, brk, Type I, 50 mm/min	100	%	ASTM D638
Tensile Modulus, 5 mm/min	2200	MPa	ASTM D638
Flexural Stress, yld, 1.3 mm/min, 50 mm span	90	MPa	ASTM D790
Flexural Modulus, 1.3 mm/min, 50 mm span	2100	MPa	ASTM D790
<b>IMPACT</b>			
Izod Impact, notched, 23°C	800	J/m	ASTM D256
Izod Impact, notched, -30°C	650	J/m	ASTM D256
Izod Impact, notched, -40°C	600	J/m	ASTM D256
Instrumented Dart Impact Total Energy, 23°C	70	J	ASTM D3763
<b>THERMAL</b>			
Vicat Softening Temp, Rate B/50	145	°C	ASTM D1525
HDT, 1.82 MPa, 3.2mm, unannealed	123	°C	ASTM D648
CTE, -40°C to 40°C, flow	6.E-05	1/°C	ASTM E831
CTE, -40°C to 40°C, xflow	6.E-05	1/°C	ASTM E831
Relative Temp Index, Elec <sup>(1)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/impact <sup>(1)</sup>	80	°C	UL 746B
Relative Temp Index, Mech w/o impact <sup>(1)</sup>	80	°C	UL 746B
<b>PHYSICAL</b>			
Specific Gravity	1.2	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.4 – 0.8	%	SABIC method
Melt Flow Rate, 300°C/1.2 kgf	10	g/10 min	ASTM D1238
Water Absorption, 23°C/24hrs	0.15	%	SABIC method
<b>ELECTRICAL</b>			
Volume Resistivity	>1.E+15	Ω.cm	ASTM D257
Surface Resistivity	>1.E+15	Ω	ASTM D257
Dielectric Strength, in oil, 0.8 mm	15	kV/mm	ASTM D149
Relative Permittivity, 1 MHz	3	-	ASTM D150
Dissipation Factor, 1 MHz	0.0093	-	ASTM D150
Hot-Wire Ignition (HWI), PLC 3	≥3	mm	UL 746A
<b>FLAME CHARACTERISTICS <sup>(1)</sup></b>			

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
UL Yellow Card Link	<u>E207780-100651927</u>	-	-
UL Recognized, 94HB Flame Class Rating	≥0.75	mm	UL 94
Glow Wire Ignitability Temperature, 3.0 mm	875	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.5 mm	875	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 1.0 mm	875	°C	IEC 60695-2-13
Glow Wire Ignitability Temperature, 0.75 mm	850	°C	IEC 60695-2-13
Glow Wire Flammability Index, 3.0 mm	960	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.5 mm	850	°C	IEC 60695-2-12
Glow Wire Flammability Index, 1.0 mm	850	°C	IEC 60695-2-12
Glow Wire Flammability Index, 0.75 mm	825	°C	IEC 60695-2-12
<b>INJECTION MOLDING <sup>(2)</sup></b>			
Drying Temperature	120	°C	
Drying Time	3 – 4	Hrs	
Drying Time (Cumulative)	48	Hrs	
Maximum Moisture Content	0.02	%	
Melt Temperature	295 – 315	°C	
Nozzle Temperature	290 – 310	°C	
Front - Zone 3 Temperature	295 – 315	°C	
Middle - Zone 2 Temperature	280 – 305	°C	
Rear - Zone 1 Temperature	270 – 295	°C	
Mold Temperature	70 – 110	°C	
Back Pressure	0.3 – 0.7	MPa	
Screw Speed	40 – 70	rpm	
Shot to Cylinder Size	40 – 60	%	
Vent Depth	0.025 – 0.076	mm	

(1) UL Ratings shown on the technical datasheet might not cover the full range of thicknesses and colors. For details, please see the UL Yellow Card.

(2) Molding conditions are only mentioned as general guidelines, need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.