

NORYL™ RESIN FE1520PW

REGION AMERICAS

DESCRIPTION

NORYL FE1520PW resin is a 20% glass fiber reinforced blend of polyphenylene ether (PPE) + polystyrene (PS). This injection moldable material is FC EU, FDA food contact compliant*, NSF/ANSI 61, ACS, WRAS and KTW-WBGL listing** for global potable water use for specific colors is available. NORYL FE1520PW resin exhibits excellent long term hydrolytic stability, very low moisture absorption, heat / hot water resistance and is an excellent candidate for a variety of water management applications such as pump housings, impellers, shower/faucet, membrane housings and valves.

* Restrictions may apply in the case of applications involving fatty foods. Please review the food contact declaration for details.

** Potable water listing is color dependent

| GENERAL INFORMATION | |
|---------------------------|--|
| Features | Hydrolytic Stability, Low Warpage, Amorphous, Low Shrinkage, Low Corrosivity, Low Moisture Absorption, Low Specific Gravity, Food contact, Potable water safe, Dimensional stability, High stiffness/Strength, No PFAS intentionally added |
| Fillers | Glass Fiber |
| Polymer Types | Polyphenylene Ether + PS (PPE+PS) |
| Processing Techniques | Injection Molding |
| INDUSTRY | SUB INDUSTRY |
| Building and Construction | Water Management |
| Hygiene and Healthcare | Personal and Professional Hygiene |

TYPICAL PROPERTY VALUES

Revision 20240325

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-----------|--------------|
| MECHANICAL ⁽¹⁾ | | | |
| Tensile Stress, brk, Type I, 5 mm/min | 119 | MPa | ASTM D638 |
| Tensile Strain, brk, Type I, 5 mm/min | 2.6 | % | ASTM D638 |
| Tensile Modulus, 5 mm/min | 7100 | MPa | ASTM D638 |
| Flexural Stress, brk, 1.3 mm/min, 50 mm span | 175 | MPa | ASTM D790 |
| Flexural Modulus, 1.3 mm/min, 50 mm span | 6970 | MPa | ASTM D790 |
| Taber Abrasion, CS-17, 1 kg | 65 | mg/1000cy | SABIC method |
| Tensile Stress, break, 5 mm/min | 119 | MPa | ISO 527 |
| Tensile Strain, break, 5 mm/min | 2.6 | % | ISO 527 |
| Tensile Modulus, 1 mm/min | 7170 | MPa | ISO 527 |
| Flexural Stress, break, 2 mm/min | 165 | MPa | ISO 178 |
| Flexural Modulus, 2 mm/min | 6040 | MPa | ISO 178 |
| Ball Indentation Hardness, H358/30 | 220 | MPa | ISO 2039-1 |
| IMPACT ⁽¹⁾ | | | |
| Izod Impact, unnotched, 23°C | 400 | J/m | ASTM D4812 |
| Izod Impact, unnotched, -30°C | 395 | J/m | ASTM D4812 |
| Izod Impact, notched, 23°C | 65 | J/m | ASTM D256 |
| Izod Impact, notched, -30°C | 45 | J/m | ASTM D256 |

| PROPERTIES | TYPICAL VALUES | UNITS | TEST METHODS |
|--|----------------|-------------------------|--------------|
| Izod Impact, unnotched 80*10*4 +23°C | 25 | kJ/m ² | ISO 180/1U |
| Izod Impact, unnotched 80*10*4 -30°C | 23 | kJ/m ² | ISO 180/1U |
| Izod Impact, notched 80*10*4 +23°C | 6 | kJ/m ² | ISO 180/1A |
| Izod Impact, notched 80*10*4 -30°C | 4 | kJ/m ² | ISO 180/1A |
| Charpy Impact, notched, 23°C | 6 | kJ/m ² | ISO 179/2C |
| Charpy -30°C, V-notch Edgew 80*10*4 sp=62mm | 5 | kJ/m ² | ISO 179/1eA |
| Charpy Impact, notched, -30°C | 27 | kJ/m ² | ISO 179/2C |
| Charpy 23°C, Unnotch Edgew 80*10*4 sp=62mm | 30 | kJ/m ² | ISO 179/1eU |
| THERMAL ⁽¹⁾ | | | |
| HDT, 1.82 MPa, 3.2mm, unannealed | 135 | °C | ASTM D648 |
| CTE, -40°C to 40°C, flow | 3.E-05 | 1/°C | ISO 11359-2 |
| CTE, -40°C to 40°C, xflow | 7.E-05 | 1/°C | ISO 11359-2 |
| Vicat Softening Temp, Rate A/50 | 150 | °C | ISO 306 |
| Vicat Softening Temp, Rate B/120 | 144 | °C | ISO 306 |
| HDT/Be, 0.45MPa Edgew 120*10*4 sp=100mm | 139 | °C | ISO 75/Be |
| HDT/Ae, 1.8 MPa Edgew 120*10*4 sp=100mm | 132 | °C | ISO 75/Ae |
| PHYSICAL ⁽¹⁾ | | | |
| Moisture Absorption, (50% RH, Equilibrium) | 0.06 | % | ASTM D570 |
| Mold Shrinkage, flow, 3.2 mm ⁽²⁾ | 0.2 – 0.4 | % | SABIC method |
| Mold Shrinkage, xflow, 3.2 mm ⁽²⁾ | 0.3 – 0.6 | % | SABIC method |
| Density | 1.24 | g/cm ³ | ISO 1183 |
| Water Absorption, (23°C/saturated) | 0.2 | % | ISO 62-1 |
| Melt Volume Rate, MVR at 280°C/10.0 kg | 22 | cm ³ /10 min | ISO 1133 |
| INJECTION MOLDING ⁽³⁾ | | | |
| Drying Temperature | 100 – 120 | °C | |
| Drying Time | 2 – 4 | Hrs | |
| Maximum Moisture Content | 0.02 | % | |
| Melt Temperature | 290 – 320 | °C | |
| Nozzle Temperature | 290 – 320 | °C | |
| Front - Zone 3 Temperature | 300 – 310 | °C | |
| Middle - Zone 2 Temperature | 280 – 300 | °C | |
| Rear - Zone 1 Temperature | 270 – 280 | °C | |
| Hopper Temperature | 60 – 80 | °C | |
| Mold Temperature | 80 – 120 | °C | |

(1) The information stated on Technical Datasheets should be used as indicative only for material selection purposes and not be utilized as specification or used for part or tool design.

(2) Measurements made from laboratory test coupon. Actual shrinkage may vary outside of range due to differences in processing conditions, equipment, part geometry and tool design. It is recommended that mold shrinkage studies be performed with surrogate or legacy tooling prior to cutting tools for new molded article.

(3) Injection Molding parameters are only mentioned as general guidelines. These may not apply or may need adjustment in specific situations such as low shot sizes, large part molding, thin wall molding and gas-assist molding.

ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.



DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.