

Noryl* Resin WCP761

Asia Pacific: COMMERCIAL

Flexible Noryl injection molding grade. Low specific gravity with very good non-halogenated flame retardant performance. Developed for evaluation in overmolding applications such as plugs, strain relief's, and connectors. UL94 V-0 performance with good processability.

Property

TYPICAL PROPERTIES ⁽¹⁾			
MECHANICAL	Value	Unit	Standard
Tensile Stress, brk, Type I, 50 mm/min	7	MPa	ASTM D 638
Tensile Strain, brk, Type I, 50 mm/min	165	%	ASTM D 638
Flexural Modulus, 12.5 mm/min, 100 mm span	50	MPa	ASTM D 790
Hardness, Shore A, 30S reading	78	-	ASTM D 2240
Tensile Stress, break, 50 mm/min	8	MPa	ISO 527
Tensile Strain, break, 50 mm/min	165	%	ISO 527
Flexural Modulus, 12.5 mm/min	40	MPa	ISO 178
Tear strength	16	N/mm	ISO 6383
IMPACT	Value	Unit	Standard
Brittleness Temperature	<-40	°C	ASTM D 746
PHYSICAL	Value	Unit	Standard
Specific Gravity	1.05	-	ASTM D 792
Water Absorption, 23°C/48hrs	0.1	%	ASTM D 570
Mold Shrinkage, flow, 24 hrs	1.08	%	ASTM D 955
Mold Shrinkage, xflow, 24 hrs	1.1	%	ASTM D 955
Melt Flow Rate, 210°C/5 kgf	14.5	g/10 min	ASTM D 1238
Melt Flow Rate, 250°C/2.16 kgf	20	g/10 min	ASTM D 1238
ELECTRICAL	Value	Unit	Standard
Volume Resistivity	1.3E+16	Ohm-cm	ASTM D 257
Dielectric strength in oil, 2.0mm	25	kV/mm	IEC 60243-1
Relative Permittivity, 1 MHz	2.5	-	IEC 60250
Dissipation Factor, 1 MHz	0.002	-	IEC 60250
Comparative Tracking Index	600	V	IEC 60112
FLAME CHARACTERISTICS	Value	Unit	Standard
UL Recognized, 94V-0 Flame Class Rating (3)	6	mm	UL 94
Glow Wire Flammability Index 960°C, passes at	3	mm	IEC 60695-2-12
Glow Wire Ignitability Temperature, 3.0 mm	775	°C	IEC 60695-2-13
Oxygen Index (LOI)	24	%	ISO 4589

Source GMD, last updated:04/21/2008

Processing

Parameter	Value	Unit
Injection Molding		
Drying Temperature	65 - 75	°C
Drying Time	4 - 6	hrs
Drying Time (Cumulative)	8	hrs
Maximum Moisture Content	0.01	%
Melt Temperature	220 - 250	°C

Nozzle Temperature	220 - 250	°C
Front - Zone 3 Temperature	220 - 250	°C
Middle - Zone 2 Temperature	210 - 240	°C
Rear - Zone 1 Temperature	180 - 220	°C
Mold Temperature	40 - 60	°C
Back Pressure	3 - 10	MPa
Screw Speed	30 - 80	rpm
Shot to Cylinder Size	30 - 70	%
Vent Depth	0.03 - 0.05	mm

Source GMD, last updated:04/21/2008

THESE PROPERTY VALUES ARE NOT INTENDED FOR SPECIFICATION PURPOSES.

PLEASE CHECK WITH YOUR [\(LOCAL SALES OFFICE\)](#) FOR AVAILABILITY IN YOUR REGION

- (1) Typical values only. Variations within normal tolerances are possible for various colors. All values are measured after at least 48 hours storage at 23°C/50% relative humidity. All properties, except the melt volume and melt flow rates, are measured on injection molded samples. All samples tested under ISO test standards are prepared according to ISO 294.
- (2) Only typical data for selection purposes. Not to be used for part or tool design.
- (3) This rating is not intended to reflect hazards presented by this or any other material under actual fire conditions.
- (4) Internal measurements according to UL standards.

Disclaimer : THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE SABIC INNOVATIVE PLASTICS COMPANY, ITS SUBSIDIARIES AND AFFILIATES ("SABIC IP"), ARE SOLD SUBJECT TO SABIC IP' S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SABIC IP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (I) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING SABIC IP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SABIC IP' S STANDARD CONDITIONS OF SALE, SABIC IP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of SABIC IP' s materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating SABIC IP materials or products will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of SABIC IP' s Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by SABIC IP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of SABIC Innovative Plastics Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right

* Noryl is a trademark of the SABIC Innovative Plastics Company

© 1997-2008 SABIC Innovative Plastics Company.All rights reserved